



GASKET MATERIAL GUIDE

	Buna-N	EPDM	FLURO-ELASTOMER
Temperature	-65° to 210°F	-60° to 300°F	-20° to 350°F
Acid	Good	Good to Ex.	Good to Ex.
Akaii	Fair to Good	Good to Ex.	Poor to Good
Fats/Oils	Good to Ex.	Poor	Good to Ex.
Taste	Good	Good	Good
Odor	Good	Good	Good
Abrasion Resist	Excellent	Good	Good
Compression Test	Good	Fair	Good to Ex.

	PTFE	Silicone	Polyethylene
Temperature	-40° to 450°F	-80° to 450°F	-20° to 150°F
Acid	Good to Ex.	Poor to Good	Good
Akaii	Excellent	Poor to Fair	Good
Fats/Oils	Excellent	Poor to Good	Good
Taste	Excellent	Good	Excellent
Odor	Excellent	Good	Excellent
Abrasion Resist	Fair	Poor	Fair
Compression Test	Cold Flows	Good to Ex.	Cold Flows